



# KLINGER<sup>®</sup>Quantum – unique gasket material with highest flexibility at high temperatures with FDA conformity.

Characterized by a high-quality fiber and filler compound bonded in an HNBR matrix, this unique gasket material offers greatest flexibility at high temperatures.

KLINGER<sup>®</sup>Quantum is the preferred choice for use with oils, water, steam, gases, salt solutions, fuels, alcohols, moderate organic and inorganic acids, hydrocarbons, lubricants as well as refrigerants.

Quantur Quant Quan Quan Quan Quan Quan
Onaliting Onaliting Onaliting Onaliting Onaliting Onaliting Onaliting
C pushtin Quantitin Quantitin
Quan Quan Quan Qua
atti Qualitati Qualitati Qualitati Qualitati
mannin Quantum Quantum Quantum Q
Quantum Quantum Quantum Quantum Quantum
atturn atturn atturn attainin anatturn
The strength with the strength strength and

Basis composition	High-quality fiber and filler compound bonded in a high-temperature	Sheet size
	resistant HNBR-Matrix.	Thicknes
Color	White	
Certificates	Oxygen-tested, DIN-DVGW, TA-Luft (Clean air), Fire-Safe acc. to DIN EN ISO 10497, FDA conformity	<b>Tolerance</b> Thickness Length: Width:

Sheet size	2000 x 1500 mm
Thickness	0.8 mm, 1.0 mm, 1.5 mm, 2.0 mm, 3.0 mm
Tolerances	
	according to DIN 28091-1


## Industry

General industry / Chemical / Oil & Gas / Energy / Infrastructure / Pulp & Paper / Marine / Automotive / Food & Beverage / Pharma


# TECHNICAL DATA – Typical values for a thickness of 2.0 mm

Compressibility	ASTM F 36 J	%	10
Recovery	ASTM F 36 J	%	50
Stress relaxation DIN 52913	50 MPa, 16 h/175°C	MPa	32
	50 MPa, 16 h/300°C	MPa	30
Stress relaxation BS 7531	40 MPa, 16 h/300°C	MPa	29
KLINGER cold/hot compression	thickness decrease at 23°C	%	10
50 MPa	thickness decrease at 300°C / 400°C	%	14 / 20
Tightness	DIN 28090-2	mg/(s x m)	0.02
Specific leakrate	VDI 2440	mbar x l/(s x m)	4.4E-08
Thickness increase after fluid	oil IRM 903: 5 h/150°C	%	3
immersion ASTM F 146	fuel B: 5 h/23°C	%	5
Density		g/cm <sup>3</sup>	1.7
Average surface resistance	Οq	Ω	7.7x10E12
Average specific volume resistance	D	Ω cm	4.7x10E12
Average dielectric strength	Ed	kV/mm	18.5
Average power factor	50 Hz	tan δ	0.064
Average dielectric coefficient	50 Hz	εr	6.8
Thermal conductivity	λ	W/mK	0.44
Classification acc. to BS 7531:2006	Grade AX		
ASME-Code sealing factors			
for gasket thickness 2.0 mm	tightness class 0.1mg/s x m	MPa	y 15
			m 2.5





# **Tightness performance**



### The tightness performance graph

The graph shows the required stress at assembling to seal a certain tightness class. The determination of the graph is based on EN13555 test procedure which applies 40 bar Helium at room temperature. The sloping curve indicates the ability of the gasket to increase tightness with raising gasket stress.

# Chemical resistance chart

Simplified overview of the chemical resistance depending on the most important groups of raw materials:

#### **KLINGER®Quantum** A: small or no attack B: weak till moderate attack C: strong attack Chlorinated Paraffinic Moto Motor Mineral Acid Base Aromates Alcohol Ketone Ester Water hydrocarbon (diluted) hydrocarbon fuel oil lubricants (diluted) fluids Α в С С Α в Α С С Α Α Α

For more information on chemical resistance please visit www.klinger.co.at.

All information is based on years of experience in production and operation of sealing elements. However, in view of the wide variety of possible installation and operating conditions one cannot draw final conclusions in all application cases regarding the behaviour in gasket joint. The data may not, therefore, be used to support any warranty claims. This edition cancels all previous issues. Subject to change without notice.



Certified acc. to DIN EN ISO 9001:2015 Subject to technical alterations. Status: December 2024 Rich. Klinger Dichtungstechnik GmbH & Co KG / Am Kanal 8-10 / A-2352 Gumpoldskirchen, Austria Tel +43 (0) 2252/62599-137 / Fax +43 (0) 2252/62599-296 / e-mail: marketing@klinger.co.at

#### www.klinger.co.at